

TRAFOL IEC UN

TRAFOL IEC UN is an Uninhabited Transformer Oil meeting the IEC 60296 Edition 5 (2020) specifications and is type B TVBU. It possesses excellent electrical and oxidation stability characteristics.

S. No.	Characteristic	Unit	Test Method	Guaranteed Data	
				Min.	Max.
A.	Function				
1	Viscosity at 40°C	cSt	ISO 3104		12
2	Viscosity at -30°C	cSt	ISO 3104		1800
3	Pour Point	°C	ISO 3016		- 40
4	Water Content, Bulk/ Drum	ppm	IEC 60814		30/40
5	Breakdown Voltage		IEC 60156		
	As delivered/ After treatment	kV		30 / 70	
6	Density at 20°C	g/ml	ISO 3675 or ISO 12185		0.895
7	DDF at 90°C	-	IEC 60247 or IEC 61620		0.005
B.	Refining/ Stability				
8	Colour	-	ISO 2049		1.5
9	Appearance	-	-	Clear, free from sediment and suspended matter	
10	Acidity	mgKOH/gm	IEC 62021-1 or -2		0.01
11	Interfacial tension	mN/m	EN 14210 or ASTM D971	40	
12	Corrosive Sulphur	-	DIN 51353	Not corrosive	
13	Potential Corrosive Sulphur	-	IEC 62535	Not corrosive	
14	DBDS	mg/Kg	IEC 62697 -1 (in prep.)	Not detectable (<5)	
15	Antioxidants	%	IEC 60666	Not detectable (<0.01)	
16	Metal passivator additives	mg/Kg	IEC 60666	Not detectable (<5)	
17	Other additives	-		Does not contain any other additives	
18	2-Furural and related compounds content	mg/Kg	IEC 61198	Not detectable (<0.05) for each individual compound	
C.	Performance				
19	Oxidation Stability		IEC 61125:1992 (Method C) Test duration — (I) Inhibited Oil 500 hrs.		
a)	Total acidity	mgKOH/gm	1.9.4 of IEC 61125:1992		1.2
b)	Sludge	%	1.9.1 of IEC 61125:1992		0.8
c)	DDF at 90°C	-	1.9.6 of IEC 61125:1992, Amendment 1 (2004)+ IEC 60247		0.5
D.	Health, Safety and Environment (HSE)				
20	Flash Point	°C	ISO 2719	135	
21	PCA content	%	IP 346		3
22	PCB content	mg/Kg	IEC 61619	Not detectable (<2)	

Disclaimer: Manufacturer makes no warranties, representation or conditions of any kind, expressed or implied, for use with respect to these products. Final determination of suitability of these products for the application contemplated by the user is solely the user's responsibility.